

ARBO 2650 Primer

Arbo 2650 Primer is a one part, solvent containing, air-drying polyacrylate/silane blend based primer.

MAIN APPLICATIONS

Recommended for use in conjunction with the Arbosil Silicone and Arbomeric MP ranges of products for the priming of porous surfaces such as concrete, block-work, brickwork etc.

APPLICATION INSTRUCTIONS

The joint surfaces must be clean, dry and free from all contamination. The surfaces should be degreased using the appropriate Arbo Cleaner. Apply one coat of Arbo 2650 Primer using a clean dry brush and allow it to dry for a least 1 hour but not more than 8 hours before applying the sealant.

All joint preparation and priming should be carried out in accordance with BS 8000 Part 16, the British Standard for the sealing of joints in buildings using sealants.

TECHNICAL DATA

Colour:	Colourless
Density:	Approx 0.95 g/cm ³
Application Temperature:	+ 5° C to + 30° C
Cleaning:	Tools must be carefully cleaned immediately after use with an appropriate cleaner.



JOINT SIZE SUITABILITY

The joint width should be at least 6mm in order that the joint faces can be cleaned and primed correctly.

STORAGE LIFE

6 months in original unopened package stored in a cool, dry place out of direct sunlight.

HEALTH & SAFETY

Arbo 2650 Primer is labelled as Harmful and Highly Flammable. For full information please refer to Material Safety Data Sheet.

PACKAGING

Arbo 2650 Primer is supplied in 500ml containers (yield approximately 125 metres per 500ml).

IMPORTANT: The information in this leaflet is given in good faith and based on results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control. Goods are supplied subject to the Company's terms and conditions of sales, a copy of which is available on request.

CARLISLE® Adshead Ratcliffe & Co Ltd. United Kingdom

Derby Road | Belper
Derbyshire

DE56 1WJ
United Kingdom

T	+44 (0)1773 826661	E	arbo@arbo.co.uk
F	+44 (0)1773 821215		www.arbo.co.uk